


Bona Sport®

Wood Sport Floor Finishes

Finish Base	Resin	Solids	VOC g/L	Coverage/ Gallon	Dry Time	2-component	Durability	Leveling	Intercoat Abrasion
	Bona® SuperSport HD								
Water	Polymeric	30%	275	500-600 sq.ft.	2-3* HRS	YES			NO**
	Bona® SuperSport								
Water	Polymeric	28%	350	500-600 sq.ft.	2-3* HRS	YES			NO**
	Bona SuperSport ONE®								
Water	Polymeric	32.5%	145	500-600 sq.ft.	2-3* HRS	NO			NO**
	Bona Sport® Poly 350™								
Oil	Oil-Modified Polyurethane	55%	350	600 sq.ft.	18-24* HRS	NO			YES
	Bona Sport® Poly								
Oil	Oil-Modified Polyurethane	50%	450	600 sq.ft.	12-16* HRS	NO			YES
	Bona All Court® Poly								
Oil	Oil-Modified Polyurethane	43%	500	600 sq.ft.	8-12* HRS	NO			YES

* Environmental jobsite conditions (Temp and RH) can vary dry times
 ** No abrasion needed if coated within 48 hours of initial coat




All Bona SuperCourt Finishes are **MFMA approved.**



Bona's industry-leading waterborne finishes are **GREENGUARD Gold Certified** for indoor air quality.

Bona Sport[®]

Wood Sport Floor Finishes



THE BONA SYSTEM™: SPORT

When you choose the Bona System for your sport floor needs, you're not only getting superior product solutions for the installation, renovation and maintenance of your sport floors, you're also receiving the best service and expertise in the industry. Our Bona Sport team has over 125 years of combined experience, making us the leading experts for all your flooring needs.